



THE RESITECH GROUP

Shed 20A/17 River Road REDBANK QLD 4301 PO BOX 3116 BIRKDALE QLD 4159

Phone: 07 3822 8233 Fax: 07 3207 5971 Email: info@theresitechgroup.com

Specialists in Plastics Recycling & Plastic Sheet Extrusion Products

TECHNICAL DATA SHEET

"DRY-ROOT" ROOT BARRIER PRODUCT

DESCRIPTION:

"Dry-Root" Root Barrier is a Polymeric Membrane for the protection against the unwanted intrusion of tree roots and moisture seepage in prevention of kerb, driveway, and house foundation damage.

The 'DRY-ROOT' root control barrier is a waterproof flexible membrane made from High Density Polyethylene plastic and stabilised to comply with Australian Standards to ASTM D5199/1505.

This product will allow for trees to remain and exist along-side of buildings, driveways and paths without causing any underground problems.

AREAS OF USE:

"Dry-Root: root barrier is suitable for the following suitable applications:

- New or existing roadway constructions
- Protection of concrete paths and pipes etc,
- Landscaping applications,
- Protection from tree roots.

FEATURES AND BENEFITS:

- Rigid barrier for ease of use when creating a vertical root barrier,
- Chemically inert,
- Available in a range of roll lengths, thicknesses and widths,
- Easy to use,
- Australian Made to Australian conditions,
- Permanent Life-span as non-degradable,
- Cost effective.
- A Recyclable product back to Resitech Recycling.

PACKAGING AND STORAGE:

- 'DRY-ROOT' rolls available singular or pallet quantities,
- Product is labelled with a DRY-ROOT identification,
- Sizes available from:
- 300mm – 1200 width,
- 750um – 2000um thickness,
- 20m – 100m length.



THE RESITECH GROUP

Shed 20A/17 River Road REDBANK QLD 4301 PO BOX 3116 BIRKDALE QLD 4159

Phone: 07 3822 8233 Fax: 07 3207 5971 Email: info@theresitechgroup.com

Specialists in Plastics Recycling & Plastic Sheet Extrusion Products

HEALTH AND SAFETY:

- Avoid Excessive Heat,
- Lift with care due to product weight as per specification sheet.
- Unroll with care as roll edges may be sharp.
- Refer to the Material Safety Data Sheet from Resitech for more details.

TECHNICAL DATA:

<u>PHYSICAL PROPERTIES</u>			
<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>VALUE</u>	<u>UNITS</u>
DENSITY	ASTM D1505/D2839	0.945	G/CM3
TENSILE STRENGTH	ASTM D638	27	MPa
ELONGATION AT BREAK	ASTM D638	>600	%
FLEXURAL MODULUS	ASTM D790	990	MPa
IZOD IMPACT STRENGTH @ -30°C	ASTM D256 METHOD A	250	J/m
DUROMETER HARDNESS	ASTM D2240	63	SHORE D
ESCR-100% IGEPAL (F)	ASTM D1693	>1000	HOURS
CARBON BLACK	ASTM D1603	2	%

DISCLAIMER:

The information provided by Resitech in relation to Resitech goods or their use is in good faith, which has been compiled from various sources and is believed by Resitech to be appropriate and reliable. The actual use and application of the goods will vary with application conditions which are beyond our control. Resitech makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information.